



Alternate Peel Strength Test

An ECIA Knowledge Document

Volume 1, Number 1

October 2009



NOTICE

ECIA Knowledge Documents are designed to serve the public interest through eliminating misunderstandings between manufacturers and purchasers, facilitating interchangeability and improvement of products, and assisting the purchaser in selecting and obtaining with minimum delay the proper product for his particular need. Existence of such documents shall not in any respect preclude any member or nonmember of ECIA from manufacturing or selling products not conforming to the documents, nor shall the existence of such documents preclude their voluntary use by those other than ECIA members, whether the document is to be used either domestically or internationally.

ECIA does not assume any liability to any patent owner, nor does it assume any obligation whatever to parties adopting the Document.

This Document does not purport to address all safety problems associated with its use or all applicable regulatory requirements. It is the responsibility of the user of this Document to establish appropriate safety and health practices and to determine the applicability of regulatory limitations before its use.

This ECIA Knowledge Document was formulated under the cognizance of the Automated Component Handling Standards Committee.

Published by

©Electronic Components Industry Association 2017
EIA Standards & Technology Department
2214 Rock Hill Road, Suite 265
Herndon, VA 20170

EIA/ECA Automated Component Handling Committee

Suggested Knowledge Base Entry By Bill Aldeen, 10/21/09

Alternate Peel Strength Test

EIA-481, the recognized standard for packaging Surface Mount Devices for automated handling, describes a peel strength test in Section 4.11. The purpose of the test is to determine that the cover tape is attached to the carrier tape firmly enough to hold components in the pockets, but not too firmly to inhibit peeling off during feeding.

The standard test involves peeling back the entire cover tape and measuring the force required. Both seals are peeled off simultaneously.

The alternate test involves slicing the cover tape in two lengthwise, and measuring peel strength of each seal individually. This alternate test is not part of the EIA-481 standard, but may be of interest to some users.

The recommended peel strength for both tests is shown in the table below.

All measurements to be taken using a calibrated scale	RECOMMENDED PEEL STRENGTH FOR THE FOLLOWING CARRIER TAPE SIZES		
	8 mm	12 mm to 56 mm	72 mm and wider
Standard Test: Checking both seals together (per EIA-481)	0.1 to 1.0 N (10 to 100 grams)	0.1 to 1.3 N (10 to 130 grams)	0.1 to 1.5 N (10 to 150 grams)
Alternate Test: Checking one of the two seals individually	0.1 to 0.5 N (10 to 50 grams)	0.1 to 0.65 N (10 to 65 grams)	0.1 to 0.75 N (10 to 75 grams)